



GAIL (India) Ltd.
(A Govt. of India Undertaking)
Petrochemicals Marketing Division

R35A042

Linear Low Density Polyethylene for Rotomoulding

Application: R35A042 is recommended for manufacturing water storage tanks, chemical tanks, bins, automotive parts, playground equipment, material handling parts, toys, boats, vending machines etc. It is recommended to add UV additive for outdoor color products. It provides excellent processability with optimum combination of impact toughness and ESCR.

Property	Values*	Unit	Test Method
Melt Flow Index (I ₂)	4.2	gm/10min	ASTM D1238
Density	0.935	gm/cc	ASTM D1505
Tensile Strength @ yield	190	kg/cm ²	ASTM D 638
Elongation @ yield	19	%	ASTM D 638
Flexural modulus	6000	kg/cm ²	ASTM D790
Vicat softening point	115	°C	ASTM D1525

* Typical characteristics of the product given purely as a guide. Mechanical properties were determined on compression molded samples.

Processing Guidelines:

Oven temperature: 240-280°C

Regulatory Information:

Certificate is available on request.

Packaging & Storage:

R35A042 is available in natural colour/pellet form in 25 kg strong bags made of woven fabric. The product should be stored in dry conditions at temperature below 50°C and protected from UV light.

For any technical assistance contact:

GAIL Polymer Technology Centre

B-35/36, Sector-1, Noida, UP-201301, Tel: +91-0120-2549155/156, 2549310; Fax: 011-26185941

Website: www.gailonline.com

The information, data and suggestions contained herein are to the best of our knowledge accurate and reliable. It is the ultimate responsibility of the user to ensure that the product is suited and the information is applicable to the user specific application.

Revised in Apr'2008